

Type Test Report

based on Regulation (EU) No 305/2011





Notification No.: 1008

Test Report No.:	28240343 001	Order No.:	93356030	Page 1 / 3	
Client:	JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD. No.1 Zhongtian Road, Hekou Town, Rudong County, 226463 Jiangsu Province, CHINA				
Test item:	Optical Fiber Cable				
Manufacturer and manufacturing plant:	JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD. No.1 Zhongtian Road, Hekou Town, Rudong County, 226463 Jiangsu Province, CHINA				
Identification:	ZTT 3.0mm (ZTT 0978)	Serial No.:	-		
Receipt No.:	A000170070-005	Date of receipt:	2017.07.31.		
Testing location:	TÜV Rheinland InterCert Kft. Termék üzletág Villamos laboratórium H-1132 Budapest, Váci út 48/A-B, Hungary				
Test specification:	EN 60332-1-2:2004 + A1:2015 EN 60332-1-1:2004 + A1:2015				
Test Result:	This type-test report performed by the given test specification contains - the measuring data, results and statements according to the reference of the product-type by System "1+" or "3" in Annex V. of regulation 305/2011/EU, for reasons of determination of the essential characteristics in the declaration of performance Classification: E_{ca}				
Testing Laboratory:	TÜV Rheinland InterCert Kft. Termék üzletág Villamos laboratórium H-1132 Budapest, Váci út 48/A-B, Hungary				
Tested by:	Istvánné KALLÓS testing co-worker		Checked by:	László SZÁSZIK reviewer	
2017.08.14.	Ádám BOHNERT testing co-worker		2017.08.14.		
Date	Name / Position	Signature	Date	Name / Position	Signature
Other Aspects:					
Harmonised standard: EN 50575:2014 + A1:2016 Classification standard: EN 13501-6:2014					
Throughout this report a comma is used as the decimal separator.					
Abbreviations: ok / P = passed fail / F = failed n.a. / N/A = not applicable data / D = publication of data					
This test report relates to the a. m. test item. Without permission of the test center this test report is not permitted to be duplicated in extracts.					

TÜV Rheinland InterCert Kft. – H-1132 Budapest, Váci út 48/A-B
tel.: +36/1/4611150; fax: +36/1/4611199; e-mail: tuv@hu.tuv.com – honlap: www.tuv.hu

EN 60332-1-2			
Clause	Requirement + Test	Result - Remark	Verdict
ZTT 3.0mm (ZTT 0978)			
5	Procedure		
	Sample length (600 ± 25 mm).....:	615	P
	Approx. outer diameter (mm).....:	3,0	
	Flame application time (s).....:	60	P
6	Evaulation of test results		
	Not damaged area from lower edge of the top support (min. 50 mm).....:	393	P
	Damaged area from lower edge of the top support (max. 540 mm).....:	490	P
	Flame spread H (max. 425 mm).....:	97	P

Test Type:	Test for vertical flame propagation for a single insulated wire or cable 1 kW pre-mixed flame
Standard:	EN 50575:2014 + A1:2016, EN 13501-6:2014 EN 60332-1-2:2004 + A1:2015, EN 60332-1-1:2004 + A1:2015
Cable type:	ZTT 3.0mm (ZTT 0978)
Marking:	ZTT 3.0mm Simplex Optical Fiber Cable PVC ZTT0978 2017/06/24 0490M
Manufacturer:	JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.
No. of samples:	1
Ambient temperature:	26,5 °C
Date of test:	2017.08.07.
Classification according to EN 13501-6:	E_{ca}

Photo documentation

Before test

After test

Measuring equipment list				
Device	Manufacturer	Type	Identification No.	Next calibration
Measuring tape	Stabila	BM 30W	503509	2019.09.21.
Stop-watch	Helvetia	S001	502911	2017.10.25.
Digital caliper	Mitutoyo	CD-15B	0556014003	2018.01.03.
Digital temperature and humidity meter	Testo	testo 635	023302	2018.01.24.
1 kW pre-mixed burner	MEEI	-	01629026	2018.03.14.

-END OF TEST REPORT-